



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318
(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com
Visit our Website: www.acousticalsurfaces.com

We Identify and **S.T.O.P.** Your Noise Problems

ACOUSTIC SYSTEMS
ACOUSTICAL RESEARCH FACILITY
OFFICIAL LABORATORY REPORT
AS-SA1949

Revision 1

Subject: Sound Absorption Test

Date: March 04, 2002



Contents: Sound Absorption Data, One-third Octave bands
Absorption Coefficients, One-third Octave bands
Noise Reduction Coefficient

on

R-13 UltraTouch Cotton Fiber Insulation –
Thickness 4", Type A Mounting

for

Rendered by Manufacturer and released to:
Acoustical Surfaces
123 Columbia Court North
Chaska, MN 55318

ACOUSTIC SYSTEMS ACOUSTICAL RESEARCH FACILITY is
NVLAP-Accredited for this and other test procedures

National Institute of Standards
and Technology



National Voluntary
Laboratory Accreditation Program

-
- ★ Certified copies of the Report carry a Raised Seal on every page.
 - ★ Reports may be reproduced freely if in full and without alteration.
 - ★ Results apply only to the unit tested and do not extend to other same or similar items.
 - ★ The NVLAP logo does not denote product endorsement by the U.S. Government.

415 East Saint Elmo Road Austin, Texas 78745 • PO Box 3610 (78764) • 512/444-1961 • FAX 512/444-2282 • 800/749-1460
www.acousticsystems.com • e-mail: lab@acousticsystems.com

• Soundproofing Products • Sonex™ Ceiling & Wall Panels • Sound Control Curtains • Equipment Enclosures • Acoustical Baffles & Banners • Solid Wood & Veneer Acoustical Ceiling & Wall Systems
• Professional Audio Acoustics • Vibration & Damping Control • Fire Retardant Acoustics • Hearing Protection • Moisture & Impact Resistant Products • Floor Impact Noise Reduction
• Sound Absorbers • Noise Barriers • Fabric Wrapped Wall Panels • Acoustical Foam (Egg Crate) • Acoustical Sealants & Adhesives • Outdoor Noise Control • Assistive Listening Devices
• OSHA, FDA, ADA Compliance • On-Site Acoustical Analysis • Acoustical Design & Consulting • Large Inventory • Fast Shipment • No Project too Large or Small • Major Credit Cards Accepted

INTRODUCTION

“The sound absorption coefficient is a property of the material composing the surface. It is ideally defined as the fraction of the randomly incident sound power absorbed by the surface.” [ASTM C 423]

Note: Revision 1 of this report is being issued to correct the specimen description. No other information or data has been altered. Revision 1 supersedes and replaces Revision 0.

APPLICABLE STANDARDS

ASTM C 423 - 90a “Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method”.

ASTM E 795 - 93 “Standard Practices for Mounting Test Specimens during Sound Absorption Tests”.

TEST SPECIMEN

The test specimen consisted of composition acoustic material whose overall dimensions were: 2438 mm in width by 2438 mm in length by 102 mm in depth [96 x 96 x 4 inches]. The test specimen was designed, manufactured, submitted for test, and designated “R-13 UltraTouch Natural Cotton Fiber Insulation (Thickness of 4”)” by Manufacturer for Acoustical Surfaces Inc. 123 Columbia Court North, Suite 201, Chaska MN 55318. The test specimen was provided in two (2) equal pieces of nominal dimension 1219 mm by 2438 mm by 102 mm [48 x 96 x 4 inches], having a density of 24 kg/m³ [1.5 pounds per cubic foot]. At the request of the client, additional details of the material’s composition are withheld from this report for the purposes of safeguarding proprietary control over this product. (These construction details remain as part of the controlled test file to fulfill test specimen documentation requirements.)

The weight of the test specimen was 18.9 kg [41.5 pounds]. The test specimen was tested in a **Type A Mount** in strict accordance with ASTM E 795 requirements. The edges were flashed with sheet metal flashings and sealed to the specimen with metal foil tape. The flashings were then sealed to the reverberation chamber floor with duct tape. The center seam of the test specimen was also sealed with metal tape.

DESCRIPTION OF TEST

The decay rate of sound [which is inversely related to sound absorption] is measured upon terminating a steady-state broadband pink noise signal in the 254 m³ reverberation chamber. Five ensemble averages containing thirty-two decays each are measured with both the test specimen inside of and removed from the chamber. The difference between these sound absorptions at a given frequency is defined as the sound absorption of the specimen. The Sound Absorption Coefficient is the Sound Absorption per unit area of the test specimen. The Noise Reduction Coefficient (NRC) is a four-frequency average of the Sound Absorption Coefficient. A rotation microphone boom and a Norsonic Instruments NI-830 Dual Channel Real Time Analyzer, computer controlled using custom software, are used for all measurements. Measurements are made in the ISO-Preferred one-third octave bands from 100 Hz to 5000 Hz. The test was conducted in strict accordance with ASTM C 423 - 90a except where noted. This test took place at ACOUSTIC SYSTEMS ACOUSTICAL RESEARCH FACILITY, Austin, Texas, on February 7, 2002.

SOUND ABSORPTION DATA

The measured Sound Absorption [in units of area] and Sound Absorption Coefficients of the test specimen at the preferred one-third octave band center frequencies are tabulated below and then presented graphically

R-13 UltraTouch Natural Cotton Fiber Insulation (Thickness 4") Type A Mounting

1/3 Octave Band Center Freq. (Hz)	Sound Absorption (m ²)	Uncertainty (+/-)	NOTES	Sound Absorption Coefficient	Uncertainty (+/-)
125	5.6	0.6	[a]	0.95	0.10
160	5.6	0.5		0.93	0.08
200	6.8	0.4		1.14	0.06
250	7.7	0.2		1.30	0.04
315	8.1	0.2		1.36	0.03
400	7.7	0.2		1.30	0.03
500	7.1	0.2		1.19	0.03
630	7.4	0.2		1.24	0.03
800	6.6	0.2		1.10	0.03
1000	6.4	0.2		1.08	0.03
1250	6.3	0.2		1.06	0.03
1600	6.3	0.2		1.06	0.03
2000	6.1	0.2		1.02	0.03
2500	5.9	0.2		1.00	0.03
3150	5.9	0.2		0.99	0.03
4000	6.0	0.2		1.00	0.03
5000	5.9	0.2		1.00	0.03
Noise Reduction Coefficient		1.15			

a) denotes empty room absorption was greater than 0.06 as required by ASTM C423. Round robin testing with other laboratories indicate results are nevertheless reliable at 125 Hz. [b] denotes that a significant effect due to changes in test chamber temperature and humidity was noted. Actual results in these bands are typically not greater than 1.00. [c] due to the very low absorption of the specimen tested, actual absorption values cannot be determined within the reverberation time uncertainties of the chamber itself. The result for this hand should be considered inconclusive.

During the test, environmental conditions in the reverberation chamber were 24.1C and 63.0% relative humidity. The precision values [±] tabulated above represent 95% probability that the true mean value lies within the stated range.

Respectfully Submitted,



Michael C. Black
 Laboratory Technical Director

R-13 UltraTouch Natural Cotton Fiber Insulation (Thickness 4")
Type A Mounting
AS-SA1949; NRC 1.15

